




DESIGN #	DRAWN BY RF	DART AEROSPACE LTD HAWKESBURY, ONTARIO, CANADA	
CHECKED #	APPROVED #	DRAWING NO. D6009	REV. A SHEET 1 OF 1
DATE 01.08.16		TITLE CROSSTUBE MATERIAL	SCALE 1:1
A	01.08.16	NEW ISSUE	

## SPECIFICATION CONTROL DRAWING

RELEASED  
01.08.17



### NOTES

- 1) D6009-XXX CROSSTUBE  
LENGTH

WHERE XXX IS LENGTH IN INCHES  
EG. 129" LONG TUBE: D6009-129

- 2) MATERIAL: 3.500 OD x 0.625 WALL 7075-T6/T6511 (WW-T-700/7 OR QQ-A-225/9 OR QQ-A-200/11) SEAMLESS ALUMINUM TUBE.  
MINIMUM ULTIMATE TENSILE STRENGTH = 77 ksi  
MINIMUM YIELD TENSILE STRENGTH = 66 ksi
- 3) TOLERANCES ARE PER ASTM B210 AS FOLLOWS:  
O.D.:  $\pm 0.008$  MEAN ( $\pm 0.016$  INCLUDING OVALITY)  
WALL:  $\pm 0.020$  MEAN ( $\pm 0.063$  INCLUDING ECCENTRICITY)  
LENGTH: XXX  $+0.188/-0.000$   
STRAIGHTNESS: 0.010" DEVIATION / 12" LENGTH
- 4) EXTREME CARE MUST BE TAKEN TO PROTECT THE OUTSIDE SURFACE OF THE TUBE. THE OUTSIDE SURFACE MUST BE SMOOTH AND FREE FROM SURFACE DEFECTS SUCH AS SCRATCHES, NICKS, OR DENTS. DEFECTS UP TO 0.005" MAY BE BLENDED OUT LONGITUDINALLY. CIRCUMFERENTIAL GRIND MARKS ARE UNACCEPTABLE.
- 5) CHEMICAL CONVERSION COAT PER DART QSI 005 4.1

Copyright © 2001 by DART AEROSPACE LTD

THIS DOCUMENT IS PRIVATE AND CONFIDENTIAL AND IS SUPPLIED ON THE EXPRESS CONDITION THAT IT IS NOT TO BE USED FOR ANY PURPOSE OR COPIED OR COMMUNICATED TO ANY OTHER PERSON WITHOUT WRITTEN PERMISSION FROM DART AEROSPACE LTD.